



ARLON

# ▶ Ultimate PremiumPlus™ With Automotive-X



Ultimate PremiumPlus™ is an ultra-conformable cast automotive restyling color change film that is offered in multiple finishes and textures. The unique films provide exceptional conformability even on deep recesses and channels. The repositionable pressure-sensitive adhesive system is designed to perform well on new and smooth surface OEM vehicle paint. Ultimate PremiumPlus now has Automotive-X Technology to allow installers the benefit of a bubble-free installation. The vast array of colors and finishes allow you to customize your vehicle with special effects while maintaining a professional look and finish. Ultimate PremiumPlus is available in 60-inch widths for a one-piece application on a hood, roof and side panels. Customizing a vehicle body color or finish couldn't be easier. Ultimate PremiumPlus is rated for outdoor durability up to 3 to 6 years and up to 7 years for indoor graphics\*.

## ARLON RECOMMENDATIONS

Recommended post-heat surface temperature of vinyl installed: 203°F to 221°F (95°C to 105°C). Post heat must be applied gradually and approximately 5" from the film in order to avoid the matte from turning glossy.

## APPLICATIONS & FEATURES

- Unique cast vinyl wrap for Matte, Matte Effects, Satin or Gloss finishes (Silver Chrome\* and Candy Colors).
- Ease of handling and installation while maintaining softness over time.
- Designed for full vehicle^ wraps.
- Warrantied for use on rivets, corrugations and channel structures\*.

## PERFORMANCE & PHYSICAL DATA

PROPERTY	TEST METHODS	TYPICAL VALUE	
<b>SURFACE FINISH</b>	Gloss Meter 60° Reflection	Up to 10 Gloss Units (Carbon Fiber & Brushed Metal) 85 Gloss Units (Silver Chrome & Candy Colors) 10 Gloss Units (Matte) 19 to 30 Gloss Units (Satin)	
<b>THICKNESS</b>	Micrometer, Federal Bench Type	3.5-mil (89 micron) Candy Colors 3.5-mil (89 micron) Satin Colors 4-mil (100 micron) Matte Colors 4-mil (100 micron) Silver Chrome 4-mil (102 micron) Brushed Metal 5.4-mil (137 micron) Carbon Fiber	
<b>TENSILE STRENGTH</b>	Tensile Tester 2-in (51 mm) jaw separation; crosshead speed of 12 in/min. (5.1 mm/s)	≥ 12.4 lb/in	≥ 2.21 kg/cm
<b>ELONGATION</b>	Instron Tensile Tester as above	≥ 150% Black and White Films ≥ 80% all other colors and finishes	
<b>SHELF LIFE (IN BOX)</b>	Ideal storage temperature 70°F (21°C) and 50% relative humidity	2 years from factory shipment	
<b>OPTIMUM TEMPERATURE RANGE</b>	On clean, dry substrate	70°F to 80°F	21°C to 27°C

\* 3 year outdoor durability for Candy Colors; 5 year outdoor durability for Ultimate PremiumPlus Textured Films and Silver Chrome; 6 year outdoor durability and 7 year indoor durability on Ultimate PremiumPlus Standard Finishes.

^ Chrome Effects coming in 2016. Contact your local supplier for details.

▲ For more information visit, [www.ultimatepremiumplus.com](http://www.ultimatepremiumplus.com) or [www.arlonautomotive.com](http://www.arlonautomotive.com).

◆ Complex curves and channel applications should be installed using Arlon's approved installation methods found at [www.arlon.com](http://www.arlon.com) and [www.wrapitright.com](http://www.wrapitright.com).

## PERFORMANCE & PHYSICAL DATA (cont'd)

PROPERTY	TEST METHODS	TYPICAL VALUE	
APPLICATION TEMPERATURE RANGE	On clean, dry substrate	65°F to 85°F	18°F to 29°C
SERVICE TEMPERATURE RANGE	On clean, dry substrate	-40°F to 175°F	-40°C to 79°C
DIMENSIONAL STABILITY	Shrinkage After 158°F (70°C), 48 hours aging	≤ 0.010 in	≤ 0.25 mm
PEEL ADHESION	PSTC-1, 15 min, 70°F (21°C)	≥ 3.0 lb/in	≥ 0.54 kg/cm
LINER RELEASE	TLMI Release at 90°, 300 in/min (760 cm/min)	60 g/2 in	0.024 kg/2 cm

Standard Terms and Conditions Apply

## DURABILITY

Ultimate PremiumPlus is a “premium” multi-layered film. Arlon’s basic color selections have been weather tested in a variety of rigorous direct exposure locations including Florida, Arizona and California. Custom color matches are derived only from “best weathering” pigments and stabilizer systems, incurring very high durability assurance at short development times. Some colors may vary due to nature of metallic effect. Actual horizontal weathering will be dependent on maintenance, location and elemental exposure.

Information is based on tests believed to be reliable, but neither accuracy nor completeness is guaranteed.

## STORAGE AND MAINTENANCE





Storing vinyl graphics in covered areas will help prolong the life of the vinyl by limiting its exposure to damaging elements such as sunlight and rain. Protecting a wrapped car in the garage can keep it sheltered from all types of weather and harmful pollution, both of which could wear out the horizontal surfaces of the car and cause damage to the paint underneath. Vinyl that starts to brown or show discoloration has been negatively affected by acidic pollutants and if not immediately removed could stain the paint. Taking extra steps to keep the vinyl covered when not in use will help extend the life of the vinyl and keep the car looking as good as it did when it was first wrapped.








## TERMS & CONDITIONS

*The following is made in lieu of all warranties expressed or implied:*

All statements, technical information and recommendations published by Arlon relating to Arlon products are based on tests believed to be reliable and within the accuracy of the equipment used to obtain the specific values. Their accuracy or completeness is not guaranteed and Arlon makes no warranty with regard thereto. Seller’s and manufacturer’s only responsibility shall be to replace any quantity of the product proved defective. Seller and manufacturer shall not be liable for injury, loss or damage, direct or consequential, arising out of use or the inability to use the product. Nor shall seller or manufacturer be liable for any costs or expenses incurred in the processing or printing on the product. Before using, user shall determine the suitability of the product for its intended use. User assumes all risk and liability of every nature in connection therewith. No statements or recommendations other than those contained in the technical information published by Arlon shall have force or effect unless contained in an agreement manually signed by the officers of seller and manufacturer.

October 2015

USA:  200 Boysenberry Lane, Placentia, CA 92870, USA  
 EUROPE:  North Sea Building, Gevers Deynootweg 93, 4th Floor, 2586BK Den Haag, The Netherlands  
 UK:  P6 Parklands, Heywood Distribution Park, Heywood, Lancashire OL102TT, UK  
 INDIA:  4F1 Court Chambers 35, New Marines Lines, Mumbai 400 020, India

 800 232 7161/+1 714 985 6300  800 329 2756  
 +31 70 354 4311  +31 70 355 7721  
 +44 161 884 0592  +31 70 355 7721  
 +91 99 6755 3895

arlon.com